

SARV RANG PRODUCT DATA SARV COAT 2731 VINYL TOP COAT COATINGS



DESCRIPTION

Sarv coat 2731 is a physically drying topcoat based on a vinyl copolymer resin.

OUTSTANDING CHARACTERISTICS

- High corrosion resistance
- Excellent water resistance
- Good appearance
- Good flexibility

RECOMMENDED USE

As a versatile top coat for vinyl systems on exterior steel structures exposed in moderately to severely industrial and marine corrosive environment.

SURFACE PREPARATION

The surface must be clean, dry and free from any contamination such as grease, rust, mill scale, salt and loose paint.

PHYSICAL DATA

| | |
|---------------------------|-------------------------------|
| Finish..... | Gloss, semi gloss |
| Colour..... | Upon request |
| Volume Solids..... | 30±2% |
| Specific Gravity..... | 1.20 ±0.05 gr/m ³ |
| Flash Point..... | 23°C |
| Recommended D.F.T..... | 30-50 microns |
| Theoretical coverage..... | 10-6 sqm/lit 8.33-5 sqm/kg |
| Practical Coverage..... | depends on loss factor |
| Touch dry..... | 2 hrs at 20°C |
| Hard dry..... | 1 days at 20 °C |
| Thermal Resistance..... | 80°C |
| Shelf life..... | 1 year at 25°C |
| Package..... | 20 liter container |

APPLICATION DETAILS

| | |
|------------------------------|----------------------------------|
| Application method | Air/Airless spray, Brush, Roller |
| Nozzle orifice..... | .019"-.021" |
| Nozzle pressure..... | 150 bar/2200 Psi |
| Application temperature..... | 10 - 40°C |
| Mixing ratio..... | single pack |
| Thinner/Cleaner..... | SVT-27 |
| Pot life | N/A |
| Recoat interval..... | Min 24 hrs Max 2 moths |

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار