

SARV RANG PRODUCT DATA SARV COAT 2735 VINYL RED OXIE PRIMER COATINGS



DESCRIPTION

Sarv coat 2735 is a general purpose vinyl red oxide primer based on vinyl copolymer resin.

OUTSTANDING CHARACTERISTICS

- Rust Rreventing
- Excellent sprayability
- Exellent flexibility.
- Good Resistance in midly to moderately corrosive environment

RECOMMENDED USE

As versatile primer for vinyl system on steel structures exposed in moderately to severly industrial & marine corrosive environments.

SURFACE PREPARATION

Remove oil and grease, etc. with suitable detergent. Remove salt and other contaminants by (high pressure) fresh water cleaning. Clean damaged area thoroughly by power tool cleaning to ST3 (minor areas)

Or by abrasive blasting to minimum SA2, Preferably to SA2 ½ (For repair and maintenance)

Abrasive blasting to Sa 2½, SSPC-10 (for new steel)

PHYSICAL DATA

Finish.....	Flat
Colour.....	Red-Brown
Volume Solids.....	32±2%
Specific Gravity.....	1.33 ±0.05 gr/m ³
Flash Point.....	23°C
Recommended D.F.T.....	40-60 microns
Theoretical coverage.....	8-5.33 sqm/lit 6.4 sqm/lit
Practical Coverage.....	depends on loss factor
Touch dry.....	2 hrs at 20°C
Hard dry.....	1 days at 20 °C
Shelf life.....	1 year at 25°C
Thermal Resistance.....	continuous 80°C
Package.....	20 liter container

APPLICATION DETAILS

Application method	Air/Airless spray, Brush
Nozzle orifice.....	.019"-0.021"
Nozzle pressure.....	150 bar/2200 Psi
Application temperature.....	10 - 40°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT- 27
Pot life	N/A
Recoat interval.....	Min 24 hrs Max 2 moths

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار