

SARV RANG PRODUCT DATA SARV COAT 6721 ALKYD TOPCOAT COATINGS



DESCRIPTION

Sarv coat 6721 is a versatile finish coat based on long oil alkyd resin.

OUTSTANDING CHARACTERISTICS

- Good gloss and colour retention
- Excellent sprayability
- Excellent flexibility
- Good resistance in mildly to moderate environments.

RECOMMENDED USE

As a finish coat on exterior and interior of steel structures, wood substrates and massonaries, previously primed with alkyd primers.

SURFACE PREPARATION

The surface must be clean, dry and free from any contamination such as grease, salt and loose paint.

Old primed surfaces should be roughened before repainting.

PHYSICAL DATA

Finish.....	semi gloss/ gloss
Colour.....	Upon request
Volume Solids.....	50±2%
Specific Gravity.....	1.15±0.01 gr/cm ³
Flash Point.....	33°C
Recommended D.F.T.....	40-60 microns
Theoretical coverage.....	10.4-6.9 sqm/kg
Practical Coverage.....	Depends on loss factor
Touch dry.....	3 hrs at 20°C
Hard dry.....	1 week at 20°C
Thermal Resistance.....	120°C
Shelf life	1 year at 25°C
Package.....	20 liter container

APPLICATION DETAILS

Application method.....	Air /Airless spray, Brush, Roller
Nozzle orifice.....	.019" - .021"
Nozzle pressure.....	150 bar/ 2200 Psi
Application temperature.....	10-50°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT-67
Pot life	N/A
Recoat interval.....	Min. 24 hrs. Max indefinite

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار