

**SARV RANG PRODUCT DATA SARV COAT 8736-8
2 PACK ZING RICH EPOXY PRIMER COATINGS**



DESCRIPTION

Sarv coat 8736-8 is a two component, polyamide cured epoxy primer, containing zinc dust as corrosion inhibiting pigment.

The quality meets SSSC Paint 20, 1nd class of zinc rich coating.

OUTSTANDING CHARACTERISTICS

- Suitable as prefabrication primer
- Good cutting and welding properties
- Suitable as a first coat in various paint systems.
- High resistance in moderately to severely environment.

RECOMMENDED USE

As a versatile long-life primer on steel, suitable for application on industrial structures to be exposed in medium corrosive atmospheres.

SURFACE PREPARATION

Remove oil and grease, etc. with suitable detergent. Remove salt and other contaminants by (high pressure) fresh water cleaning.

Abrasive blasting to Sa 2½ , SSPC-10 with a sharp-edged surface profile corresponding to rugotest No.3, BN9a, keane – Tator comparator, 2.0 G/S or ISO comparator, medium(G).

PHYSICAL DATA

Finish.....	Flat
Colour.....	Grey, Red grey
Volume Solids.....	45% (ASTM-D-2697)
Specific Gravity.....	2.15 kg/lit
Flash Point.....	30°C
Recommended D.F.T.....	65 microns
Theoretical coverage.....	6.9 m ² / l
Practical Coverage.....	Depends on loss factor
Touch dry.....	2-3 hrs at 20°C 1 hrs at 35°C
Fully cured.....	Seven days 20°C 6 days at 35°C
Thermal Resistance.....	140 °C
Shelf life.....	1 year at 25°C

APPLICATION DETAILS

Application method ,	Air/Application spray, Brush
Nozzle orifice.....	.017"-.021"
Nozzle pressure.....	150 bar/2200 Psi
Mixing ratio.....	A/B/ 19/1 by weight
Thinner/Cleaner.....	SVT- 87
Pot life	8 hrs at 20°C
Recoat interval min:.....	24 hrs at 20°C

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: حاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار