

# SARV RANG PRODUCT DATA SARV COAT 8821-7 EPOXY POLYAMINE ANTI-ACID FLOOR COATINGS



## DESCRIPTION

Sarv coat 8821-7 is a two component, polyamine cured, solvent free epoxy Anti-Acid floor coating.

## OUTSTANDING CHARACTERISTICS

- Excellent mechanical strength
- High oil resistance
- High chemical resistance against acids and alkalies.
- Easy application.
- High electrical conductivity

## RECOMMENDED USE

As a suitable floor coating on concrete or steel industrial floors subjected to continuous mechanical wear and where, acid, chemical solvents resistance is required.

## SURFACE PREPARATION

The surface must be clean and dry. All dirt, grease, mill-scales and any other foreign materials should be removed.

## MECHANICAL CHARACTERISTICS

(For 3 mm film thickness)

Compressive strength (BS6319 pt3)	50 N/mm <sup>2</sup>
Flexural strength (BS6319 pt7)	34 N/mm <sup>2</sup>
Foot traffic at 20°C	24 hrs
Vehicle traffic at 20°C	48 hrs

## PHYSICAL DATA

Finish.....	Gloss
Colour.....	limited
Volume Solids.....	94±2%
Specific Gravity.....	1.48±0.05 gr/cm <sup>3</sup>
Flash Point.....	32°C
Dry Film Thickness.....	1000-3000 microns
Theoretical Coverage.....	0.94- 0.31 sqm/lit 0.63-0.20 sqm/kg
Touch dry.....	8 hrs at 20°C
Hard dry.....	48 hrs at 20°C
Thermal Resistance.....	140°C
Shelf life .....	1 year at 25°C

## APPLICATION DETAILS

Application method .....	Putty Knife, Trowel
Application temperature.....	10-50°C
Mixing ratio.....	6/ 1 by weight
Pot life .....	60 min at 20°C
Recoat interval.....	Min 8 hrs Max 72 hrs

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6  
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار