

SARV RANG PRODUCT DATA SARV COAT 1862-8 COLOURED ACRYLIC SILICONE COATINGS



DESCRIPTION

Sarv coat 1862-8 is a temperature resistant, paint, based on modified silicone-acrylic resin.

OUTSTANDING CHARACTERISTICS

- Rust preventing
- Excellent sprayability.
- Excellent recoatability without stoving between coats
- Applicable over zine silicate sarv caot 1983 or directly on blasted steel.

RECOMMENDED USE

As a temperature resistant paint, for use in protection of steel surfaces subjected to temperatures up to 200°C.

SURFACE PREPARATION

Remove oil and grease, etc. with suitable detergent.

Remove salt and other contaminants by (high pressure) fresh water cleaning.

Abrasive blasting to Sa 2½, SSPC-10.

PHYSICAL DATA

Finish.....	Semi flat-Semi Gloss
Colour.....	limited Red, Black-Grey, Orange
Volume Solids.....	41±2%
Specific Gravity.....	1.05±0.05 gr/m ³
Flash Point.....	25°C
Recommended D.F.T.....	25-40 microns
Theoretical Coverage.....	16.4-10.2 sqm/lit 15.6-9.7 sqm/kg
Practical Coverage.....	Depends on loss factor
Touch dry.....	2 hours at 20°C
Hard dry.....	after thermal curing
Thermal Resistance.....	Continuous 200°C
Shelf life.....	1 year at 25°C
Packageing.....	20 liter container

APPLICATION DETAILS

Application method	Air/Airless spray, Brush
Nozzle orifice.....	.017"
Nozzle pressure.....	125 bar/1800 Psi
Mixing ratio.....	Single pack
Thinner/Cleaner.....	SVT-18
Pot life	N/A
Recoat interval min:.....	24 hrs at 20 °C
Recoat interval max:.....	(see Remarks overleaf)

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار