

SARV RANG PRODUCT DATA SARV COAT 1983-7

2 PACK INORGANIC ZINC SILICATE COATINGS



DESCRIPTION

Sarv coat 1983-7 is a 2-pack, self curing (reacting with atmospheric moisture), solvent based zinc ethyl silicate coating.

OUTSTANDING CHARACTERISTICS

- High corrosion and abrasion resistance
- Heat resistance up to 420°C.
- Suitable for use with a wide range of high performance topcoats.

RECOMMENDED USE

As a general purpose, heavy duty rust preventing primer suitable for long term protection of steel structures exposed to severely corrosive and abrasive environment .

SURFACE PREPARATION

Remove oil and grease, etc. with suitable detergent. Remove salt and other contaminants by (high pressure) fresh water cleaning.

Abrasive blasting to Sa 2½, SSPC-10 with a sharp-edged surface profile corresponding to rugotest No. 3, BN9a, Keane-Tator comparator, 2.0 G/S or ISO comparator medium.(G)

PHYSICAL DATA

Finish.....	Flat
Colour.....	Grey
Volume Solids.....	61±2%
Specific Gravity.....	2.70 ±0.05 gr/m ³
Flash Point.....	14°C
Recommended D.F.T.....	50-75 microns
Theoretical coverage.....	12.2-8.13 sqm/lit 4.43-2.95 sqm/kg
Practical Coverage.....	depends on loss factor
Touch dry.....	10 min
Hard dry.....	1 days at relative humidity up to 65-75 %
Thermal Resistance.....	continuous 400°C Non-continuous 420°C
Shelf life Liquids.....	3 months at 20°C
Powder	Indefinite

APPLICATION DETAILS

Application method	Air/Airless spray, Brush
Nozzle orifice.....	.019"-.023"
Nozzle pressure.....	100 bar/1500 Psi
Application temperature.....	10 to 40°C
Mixing ratio.....	A/B 8/25 by weight
Thinner/Cleaner.....	SVT-19
Pot life	4 hrs at 20°C

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار