

SARV RANG PRODUCT DATA SARV COAT 2729 VINYL SEALER COATINGS



DESCRIPTION

Sarv coat 2729 is a physically drying sealer based on a vinyl copolymer resin.

OUTSTANDING CHARACTERISTICS

- High corrosion resistance and weather resistance
- High chemical resistance against acids and alkalies
- With the proper topcoat it withstand splash or spillage of fresh or salt water
- Excellent penetration

RECOMMENDED USE

As a sealer coat on metal and concrete surfaces and as intermediate coat on zinc silicates to minimize popping.

SURFACE PREPARATION

For previously primed surfaces with sarv coat 1983 the surface must be clean and dry. All dirt grease, mill- scales and any other foreign materials should be removed.

PHYSICAL DATA

Finish.....	Flat
Colour.....	Non-pigmented
Volume Solids.....	36±2%
Specific Gravity.....	0.95 ±0.05 gr/m ³
Flash Point.....	23°C
Recommended D.F.T.....	20-40 microns
Theoretical coverage.....	18-9 sqm/lit
.....	18.9-9.5 sqm/kg
Practical Coverage.....	depends on loss factor
Touch dry.....	20 hrs at 20°C
Hard dry.....	16 hrs at 20 °C
Shelf life.....	1 year
Package.....	4 or 20 liter container

APPLICATION DETAILS

Application method	Air/Airless spray, Brush, Roller
Application temperature.....	10 - 40°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT-27
Pot life	N/A
Recoat interval.....	Min 4 hrs Max 2 moths

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار