

# SARV RANG PRODUCT DATA SARV COAT 2732 VINYL INTERMEDIATE COATINGS



## DESCRIPTION

Sarv coat 2732 is a physically drying topcoat based on a vinyl copolymer resin.

## OUTSTANDING CHARACTERISTICS

- High corrosion resistance
- Excellent water resistance
- Good appearance
- Good flexibility

## RECOMMENDED USE

As a versatile topcoat for vinyl systems on exterior steel structures exposed in moderately to severely industrial and marine corrosive environment.

## SURFACE PREPARATION

The surface must be clean, dry and free from any contamination such as grease, rust, mill scale, salt and loose paint.

## PHYSICAL DATA

Finish.....	Flat
Colour.....	upon request
Volume Solids.....	33±2%
Specific Gravity.....	1.35 ±0.05 gr/cm <sup>3</sup>
Flash Point.....	23°C
Recommended D.F.T.....	40-60 microns
Theoretical coverage.....	8.25-5.5 sqm/lit 6.11-4.07 sqm/kg
Practical Coverage.....	Depends on loss factor
Touch dry.....	2 hrs at 20°C
Hard dry.....	1 days at 20 °C
Thermal Resistance.....	80°C
Shelf life.....	1 year at 25°C
Package.....	20 liter container

## APPLICATION DETAILS

Application method .....	Air/Airless spray, Brush, Roller
Nozzle orifice.....	.019"-0.021"
Nozzle pressure.....	150 bar/2200 Psi
Application temperature.....	10 - 40°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT-27
Pot life .....	N/A
Recoat interval.....	Min 24 hrs Max 2 months

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6  
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار