

SARV RANG PRODUCT DATA SARV COAT 2885 VINYL ETCH PRIMER COATINGS



DESCRIPTION

Sarv coat 2885 is a two component etch primer based on polyvinyl butyral.

OUTSTANDING CHARACTERISTICS

- Excellent adhesion to nonferrous surfaces
- Fast drying, permitting immediate handling
- High corrosion resistance
- Compatibility with a wide range of topcoats

RECOMMENDED USE

As a preconstruction primer and suitable for nonferrous surfaces such as galvanized steel and aluminium, to improve performance of subsequent coats.

SURFACE PREPARATION

The surface must be clean, and dry. All dirt, grease, mill- scales and any other foreign materials should be removed. Old primed surfaces must be smoothly wire brushed.

PHYSICAL DATA

Finish.....	Flat
Colour.....	Dark Yellow
Volume Solids.....	12±2%
Specific Gravity.....	0.88 ±0.93 gr/m ³
Flash Point.....	23°C
Recommended D.F.T.....	7-13 microns
Theoretical coverage.....	28-14 sqm/lit
	29.47-14.73
sqm/kg	
Practical Coverage.....	Depends on loss factor
Touch dry.....	10 min at 20°C
Dry to handle.....	30 min at 20 °C
Shelf life.....	1 year at 25 °C
Package.....	4 & 16 liter container

APPLICATION DETAILS

Application method	Air/Airless spray, Brush, Roller
Application temperature.....	10 - 50°C
Mixing ratio.....	Base/Hardener 4/1 by weight
Thinner/Cleaner.....	SVT-28
Pot life	5 hours
Recoat interval.....	Min 6 hrs
	Max 24 moths

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار