

SARV RANG PRODUCT DATA SARV COAT 3929  
ACRYLIC EMULSION SEALER COATINGS



### DESCRIPTION

Sarv coat 3929 is a physically drying penetration primer based on acrylic emulsion resin.

### OUTSTANDING CHARACTERISTICS

- Excellent water resistance
- Good weather resistance

### RECOMMENDED USE

As a sealer on concrete & masonry substrates for interior and exterior of buildings.

### SURFACE PREPARATION

The surface must be clean, dry and free from any contamination such as grease, salt and loose paint.

### PHYSICAL DATA

Finish.....	Flat
Colour.....	clear
Volume Solids.....	12±2%
Specific Gravity.....	1.03±0.05 gr/cm <sup>3</sup>
Recommended D.F.T.....	5-10 microns
Theoretical coverage.....	24-12 sqm/lit.
	23.3-11.65
	sqm/kg
Practical Coverage.....	Depends on loss factor
Touch dry.....	30 min. at 20°C
	10 min. at 30°C
Hard dry.....	4 hrs. at 20°C
	2 hrs. at 35°C
Shelf life .....	12 months
Package.....	20 liter container

### APPLICATION DETAILS

Application method.....	Air spray, Brush, Roller
Nozzle orifice.....	.017" - .021"
Nozzle pressure.....	100 bar/ 1450 Psi
Application temperature.....	10-40°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	water
Pot life .....	N/A
Recoat interval.....	Min. 4 hrs.
	Max. Indefinite

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6  
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار