

SARV RANG PRODUCT DATA SARV COAT 6219
ALKYD UREACLEAR(VARNISH) COATINGS



DESCRIPTION

Sarv coat 6219 is a tow component clear coat based on alkyd urea formaldehyde.

OUTSTANDING CHARACTERISTICS

- Excellent scratch resistance
- Excellent hardness properties.
- Good and glossy appearance.

RECOMMENDED USE

As a clear topcoat for decorating and protecting wood surfaces. The cured film has good stain resistance against cold and hot drinks as well as washing liquids.

SURFACE PREPARATION

The surface must be clean and dry.

All dirt, grease, and any other foreign materials should be removed old primed surfaces must be smoothly brushed by sand paper.

PHYSICAL DATA

| | |
|---------------------------|-----------------------------|
| Finish..... | Gloss |
| Colour..... | no pigmented |
| Volume Solids..... | 58±2% |
| Specific Gravity..... | 1.0±0.05 gr/cm ³ |
| Flash Point..... | 25°C |
| Dry film thickness..... | 40 microns |
| Touch dry..... | 30 min at 20°C |
| Hard dry | 48 hrs |
| Theoretical coverage..... | 15 sqm/lit. 15 sqm/kg |
| Practical Coverage..... | Depends on loss factor |
| Shelf life | 12 months |
| Package..... | 4 & 20 liter container |

APPLICATION DETAILS

| | |
|------------------------------|---------------|
| Application method..... | Air Spray |
| Application temperature..... | 10-50°C |
| Thinner/Cleaner..... | SVT-62 |
| Mixing ratio..... | 7/1 by weight |
| Pot life | 8 hours |
| Recoat interval..... | --- |

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
 کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار