

# SARV RANG PRODUCT DATA SARV COAT 6722 ALKYD MIO INTERMEDIATE COATINGS



## DESCRIPTION

Sarv coat 6722 is a versatile intermediate/finish coat based on long oil alkyd resin.

## OUTSTANDING CHARACTERISTICS

- Excellent sprayability
- Good UV resistance
- Good resistance in mildly to moderate corrosive environments

## RECOMMENDED USE

As an intermediate/finish coat on exterior and interior of steel structures previous primed with alkyd primers.

## SURFACE PREPARATION

The surface must be clean, dry and free from any contamination such as grease, rust, salt and loose paint.

Old primed surfaces should be roughened.

## PHYSICAL DATA

Finish.....	Flat
Colour.....	Grey
Volume Solids.....	54±2%
Specific Gravity.....	1.45±0.05 gr/cm <sup>3</sup>
Flash Point.....	38°C
Recommended D.F.T.....	40-60 microns
Theoretical coverage.....	13.5-9 sqm/lit. 9.3-6.2 sqm/kg
Touch dry.....	18 min at 20°C 2 hrs at 35°C
Hard dry.....	1 week at 20°C
Thermal Resistance.....	continuous 120°C
Practical Coverage.....	Depends on loss factor
Shelf life .....	1 year at 25°C
Package.....	4 or 20 liter container

## APPLICATION DETAILS

Application method.....	Air /Airless spray, Brush, Roller
Nozzle orifice.....	.019" - .021"
Nozzle pressure.....	150 bar/ 2200 Psi
Application temperature.....	10-50°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT 67
Pot life .....	N/A
Recoat interval.....	Min. 24 hrs. Max 1 months

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6  
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار