

SARV RANG PRODUCT DATA SARV COAT 6729 ALKYD PHENOLIC TOPCOAT



DESCRIPTION

Sarv coat 6729 is a one component alkyd finish coat modified with phenolic.

OUTSTANDING CHARACTERISTICS

- Excellent oil resistance.
- Excellent chemical resistance against acids alkalis.
- Excellent adhesion
- Excellent weather resistance.
- Excellent Hardness
- Fast air drying.

RECOMMENDED USE

As a protection coating in industrial and marine structures over concrete or metal surface.

Resistance to a variety of chemicals , fuel oils and solvents.

As a general purpose is suitable for lining storage tanks ship tanks exposed to immersion, splash sea mater

SURFACE PREPARATION

The surface must be clean and dry . All dirt, grease, mill scales and any other foreign materials should be removed.

Old primed surfaces must be smoothly wire brushed.

Blast to sa 3 ISO 8501 or SSPC 5,the roughness profile should be 40-75 micron.

PHYSICAL DATA

Finish.....	Flat
Colour.....	Upon request
Volume Solids.....	60±2%
Specific Gravity.....	1.30±0.05 gr/cm ³
Flash Point.....	23°C
Recommended D.F.T.....	50-60 microns
Theoretical coverage.....	12-10 m ² /lit. 8-6 m ² /kg
Practical Coverage.....	Depends on loss factor
Touch dry.....	1 hrs at 25°C
Fully cured.....	4 days at 25°C
Shelf life	24 months at 20°C
Thermal Resistance.....	Continuous 120°C Non-continuous 130°C
Package.....	20 liter container

APPLICATION DETAILS

Application method.....	Air /Airless spray, Brush, Roller
Application temperature.....	10-50°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT- 67
Recoat interval.....	Min. 24 hrs. Max 72 hrs

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار