

# SARV RANG PRODUCT DATA SARV COAT 6730 FAST DRYING ALKYD TOPCOAT



## DESCRIPTION

Sarv coat 6730 is a gloss fast drying alkyd topcoat.

## OUTSTANDING CHARACTERISTICS

- Water resistance.
- Gloss and color retention.
- Excellent weather ability.
- Resistance to mild corrosive atmospheric zones

## RECOMMENDED USE

As a finish coat to be used over Sarv coat 6725 for protection as a topcoat & decorative purposes.

## SURFACE PREPARATION

The surface must be clean , dry and free from any Contamination such as grease , dirt , salt and loose paint.

Old primed surfaces should be roughened before repainting.

## PHYSICAL DATA

Finish.....	Gloss
Colour.....	Upon request
Volume Solids.....	48±2%
Specific Gravity.....	1.2±0.05 gr/cm <sup>3</sup>
Flash Point.....	24°C
Recommended D.F.T.....	40-50 microns
Theoretical coverage.....	12.5-9.6 sqm/lit. 10-8 sqm/kg
Practical Coverage.....	Depends on loss factor
Touch dry.....	15-20 minutes at 20°C
Hard dry.....	16 hrs at 20°C
Fully cured.....	14 hrs at 35°C
Shelf life .....	12 months at 20°C
Thermal Resistance.....	Continuous 90°C Non-continuous 110°C
Package.....	20 liter container

## APPLICATION DETAILS

Application method.....	Air /Airless spray, Brush, Roller
Application temperature.....	5-50°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT- 67
Pot life .....	N/A
Recoat interval.....	Min. 24 hrs. Max 1 months

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6  
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار