

SARV RANG PRODUCT DATA SARV COAT 7729 CHLORINATED RUBBER SEALER COATINGS



DESCRIPTION

Sarv coat 7729 is a sealer physically drying, modified chlorinated rubber based.

OUTSTANDING CHARACTERISTICS

- Excellent water resistance
- Durability in severe marine atmosphere
- Excellent penetration properties.

RECOMMENDED USE

As a water resistant sealer in underwater and above water systems such as ships hulls, decks and superstructures, offshores, structural steel and pipping in chemical plants, refineries, bridges and cranes.

SURFACE PREPARATION

The surface must be clean and dry. Remove oil, grease, salt and any other contamination with suitable detergent and by high pressure fresh water.

PHYSICAL DATA

Finish.....	Flat
Colour.....	non pigmented
Volume Solids.....	36±2%
Specific Gravity.....	1.23±0.05 gr/cm ³
Flash Point.....	24°C
Recommended D.F.T.....	20-40 microns
Theoretical coverage.....	18-9 sqm/lit.
	14.63-7.31
sqm/kg	
Practical Coverage.....	Depends on loss factor
Touch dry.....	15 min at 20°C
Hard dry.....	24 hours at 20°C
Thermal Resistance.....	Continuous 60° Non-continuous 65 °C
Shelf life	12 months at 25°C
Package.....	20 liter container

APPLICATION DETAILS

Application method	Air/Airless spray, Brush, Roller.
Nozzle orifice.....	.017"-0.021"
Nozzle pressure.....	150 bar/2200 Psi
Application temperature.....	10-50°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT-77
Pot life	N/A
Recoat interval.....	Min 6 hrs at 20°C

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار