

SARV RANG PRODUCT DATA SARV COAT 7731 CHLORINATED RUBBER TOP COAT COATINGS



DESCRIPTION

Sarv coat 7731 is a physically drying, modified chlorinated rubber based topcoat.

OUTSTANDING CHARACTERISTICS

- Excellent water resistance
- Durability in severe marine atmosphere
- Good penetration.

RECOMMENDED USE

As a water resistant topcoat in underwater and above water systems such as ships hulls, decks and superstructures, offshores, structural steel and pipping in chemical plants, refineries, bridges and cranes. It is also suitable for drinking water systems.

SURFACE PREPARATION

The surface must be clean, dry and free of grease, mill- scale, rust and dirt.

PHYSICAL DATA

Finish.....	Gloss, Semi gloss
Colour.....	Upon request
Volume Solids.....	38±2%
Specific Gravity.....	1.15±0.05 gr/cm ³
Flash Point.....	24°C
Recommended D.F.T.....	40-60 microns
Theoretical coverage.....	9.5-6.3 sqm/lit. 8.3-5.5 sqm/kg
Practical Coverage.....	Depends on loss factor
Touch dry.....	15 min at 20°C
Hard dry.....	2 hours at 20°C
Thermal Resistance.....	Continuous 60° Non-continuous 65 °C
Shelf life	1 year at 25°C
Package.....	20 liter container

APPLICATION DETAILS

Application method	Air/Airless spray, Brush, Roller.
Nozzle orifice.....	.017"-.021"
Nozzle pressure.....	150 bar/2200 Pai
Application temperature.....	10-50°c
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT-77
Pot life	N/A
Recoat interval.....	Min 6 hrs at 20°C

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار