

SARV RANG PRODUCT DATA SARV COAT 7733 CHLORINATED RUBBER INTERMEDIATE COATINGS



DESCRIPTION

Sarv coat 7733 is a physically drying, modified chlorinated rubber based intermediate.

OUTSTANDING CHARACTERISTICS

- Excellent water resistance
- Durability in severe marine atmosphere
- Good appearance.

RECOMMENDED USE

As a water resistant intermediate in underwater and above water systems such as ships hulls, decks and superstructures, offshores structural steel and pipping in chemical plants, bridges and cranes. It is also suitable for drinking water systems.

SURFACE PREPARATION

The surface must be clean, dry and free of grease, mill- scale, rust and dirt.

PHYSICAL DATA

Finish.....	Flat, Semi gloss
Colour.....	Upon request
Volume Solids.....	40±2%
Specific Gravity.....	1.25±0.05 gr/cm ³
Flash Point.....	24°C
Recommended D.F.T.....	40-60 microns
Theoretical coverage.....	10-6.6 sqm/lit.
.....	8-5.3 sqm/kg
Practical Coverage.....	Depends on loss factor
Touch dry.....	30 min at 20°C
Hard dry.....	24 hours at 20°C
Thermal Resistance.....	Continuous 60° Non-continuous 65 °C
Shelf life	12 months at 25°C
Package.....	20 liter container

APPLICATION DETAILS

Application method	Air/Airless spray, Bursh, Roller
Nozzle orifice.....	.017"-.021"
Nozzle pressure.....	150 bar/2200 Psi
Application temperature.....	10-50°c
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT-77
Pot life	N/A
Recoat interval.....	Min 6 hrs at 20°C

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
 کد پستی: 1473913774
 تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187
 فکس: 44037529 ایمیل: sarvrang.co@gmail.com
 آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار