

SARV RANG PRODUCT DATA SARV COAT 7988 CHLORINATED RUBBER SYNTHETIC PRIMER COATINGS



DESCRIPTION

Sarv coat 7988 is a physically quick drying synthetic primer it consist of chlorinated rubber and plasticizer and colouring matter, together with solvents needed to give a consistency suitable for application by spray, brush or other approved method. The technical data meets BS4147 Type "B" requirements.

OUTSTANDING CHARACTERISTICS

- Excellent adhesion
- Quick drying
- High water resistance.

RECOMMENDED USE

This synthetic primer for cold and hot application is used with coating materials (usually Hot Bituminous enamel, Hot coal tar enamels and cold wrapping tape) it is quick drying and application of the subsequent coating is possible within a short time.

SURFACE PREPARATION

Remove oil and grease, etc. with suitable detergent. Remove salt and other contaminants by (high pressure) fresh water cleaning. Clean damaged area thoroughly by power tool cleaning to ST2 (minor areas)

Or by abrasive blasting to minimum SA2, Preferably to Sa2½ (for repair and maintenance) Abrasive blasting to Sa 2½SSPC-10 (for new steel)

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار

PHYSICAL DATA

Finish.....	Gloss
Colour.....	Blak
Volume Solids.....	39±2%
Specific Gravity.....	0.95±0.02 gr/cm ³
Flash Point.....	24°C
Recommended D.F.T.....	30-40 microns
Theoretical coverage.....	9.6-7.5 sqm/lit. 9.47-7.1 sqm/kg
Practical Coverage.....	Depends on loss factor
Touch dry.....	10 min at 20°C
Hard dry.....	120 min at 20°C
Thermal Resistance.....	Continuous 60° Non-continuous 65 °C
Shelf life	1 year at 25°C
Package.....	20 liter container

APPLICATION DETAILS

Application method	Air/Airless spray, Brush, Roller.
Nozzle orifice.....	.017"-0.021"
Nozzle pressure.....	150 bar/2200 Psi
Application temperature.....	10-50°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT -79
Pot life	N/A
Recoat interval.....	Min 6 hrs at 20°C Max none