

SARV RANG PRODUCT DATA SARV COAT 8221 EPOXY ESTER TOP COAT COATINGS



DESCRIPTION

Sarv coat 8221 is a single pack topcoat based on epoxy ester resin.

OUTSTANDING CHARACTERISTICS

- High colour retention
- Good adhesion to previous coats.
- Toughness and durability of film.
- resistance against corrosive environments

RECOMMENDED USE

As a topcoat in industrial and marine structures such as refineries, petrochemical plants, bridges, tanks and water sewage plants.

SURFACE PREPARATION

The surface must be clean and dry. Any contamination such as dirt, grease, oil, salt and any other foreign materials should be removed.

PHYSICAL DATA

Finish.....	Gloss, Semi gloss
Colour.....	Upon request
Volume Solids.....	48±2%
Specific Gravity.....	1.2 ±0.05 gr/cm ³
Flash Point.....	23°C
Recommended D.F.T.....	40-60 microns
Theoretical coverage.....	12-8 sqm/lit 10 -6.7 sqm/kg
Partical Coverage.....	depends on loss factor
Touch dry.....	2 hrs at 20°C 1 hrs at 35°C
Hard dry.....	16 hrs at 20°C 12 hrs at 35°C
Thermal Resistance.....	continuous 100°C Non- continuous 150°C
Shelf life.....	1 year
Package.....	20 liter container

APPLICATION DETAILS

Application method	Air/Airless spray, Brush
Application temperature.....	10-50°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT-82
Pot life	N/A
Recoat interval.....	Min 24 hrs Max 3 hrs

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار