

SARV RANG PRODUCT DATA SARV COAT 8222 EPOXY ESTER INTERMEDIATE COATINGS



DESCRIPTION

Sarv coat 8222 is a single pack coating based on epoxy ester resin.

OUTSTANDING CHARACTERISTICS

- High corrosion resistance
- Good adhesion to previous and subsequent coats.
- Toughness and durability of film.
- Good temperature resistance

RECOMMENDED USE

As a intermediate or topcoat in industrial and marine structures such as refineries, petrochemical plants, bridges, tanks and water sewage plants.

SURFACE PREPARATION

The surface must be clean and dry. Any contamination such as dirt, grease, oil, salt and any other foreign materials should be removed.

PHYSICAL DATA

Finish.....	semi gloss
Colour.....	Upon request
Volume Solids.....	38±2%
Specific Gravity.....	1.33 ±0.05 gr/cm ³
Flash Point.....	23°C
Recommended.....	40-60 microns
Theoretical coverage.....	9.5-6.33 sqm/lit
	7.14 -4.76
sqm/kg	
Practical Coverage.....	depends on loss factor
Touch dry.....	60 min at 20°C
Hard dry.....	20 hrs at 20°C
Thermal Resistance.....	140°C
Shelf life.....	1 year at 25°C
Package.....	20 liter container

APPLICATION DETAILS

Application method	Air/Airless spray, Brush
Nozzle orifice.....	.019"-.023"
Nozzle pressure.....	150 bar/2200 Psi
Application temperature.....	10-50°C
Mixing ratio.....	single pack
Thinner/Cleaner.....	SVT-82
Pot life	N/A
Recoat interval.....	Min 24 hrs
	Max 3 months

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار