

SARV RANG PRODUCT DATA SARV COAT 8568 POLYAMINE CURED EPOXY VINYL TOPCOAT COATINGS



DESCRIPTION

Sarv coat 8568 is a physically drying topcoat based on a vinyl copolymer resin.

OUTSTANDING CHARACTERISTICS

- High corrosion resistance
- Excellent water resistance.
- Good appearance.
- Good flexibility.

RECOMMENDED USE

As a versatile topcoat for vinyl systems on exterior steel structures exposed in moderately to severely industrial and marine corrosive environment.

SURFACE PREPARATION

The surface must be clean, dry and free from any contamination such as grease, rust, mill scale, salt and loose paint.

PHYSICAL DATA

Finish.....	Gloss, semi gloss
Colour.....	Upon request
Volume Solids.....	41±2%
Specific Gravity.....	1.1 ±0.05 gr/cm ³
Flash Point.....	25°C
Recommended D.F.T.....	30-50 microns
Theoretical coverage.....	13.6-8.2 sqm/lit 12.4-7.45 sqm/kg
Practical Coverage.....	depends on loss factor
Touch dry.....	Max 2 hrs at 20°C
Fully cured.....	7 days at 20°C
Thermal Resistance.....	140°C
Shelf life.....	1 year at 25°C
Package.....	5& 20 liter container

APPLICATION DETAILS

Application method	Air/Airless spray, Brush
Nozzle orifice.....	.021"
Nozzle pressure.....	150 bar/2200 Psi
Application temperature.....	5-50°C
Mixing ratio.....	4/1 by weight
Thinner/Cleaner.....	SVT- 85
Pot life	8 hrs at 20°C
Recoat interval.....	Min 24 hrs Max 4 months

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار