

SARV RANG PRODUCT DATA SARV COAT 8729-7 EPOXY POLYAMIDE SEALER/FULLER COATINGS



DESCRIPTION

Sarv coat 8729-7 is a two component, polyamide cured epoxy sealer.

OUTSTANDING CHARACTERISTICS

- Excellent penetration
- High chemical & solvent resistance
- With the proper topcoat it withstands splash or spillage of water.

RECOMMENDED USE

As a sealer coat on metal surfaces, concrete and as a tie coat on ethyl silicate primer.

SURFACE PREPARATION

The surface must be clean & dry. All dirt, Grease, mill scales and any other foreign materials should be removed.

In the case of flooring the surface shall be scraped by appropriate tools.

PHYSICAL DATA

Finish.....	Glossy
Colour.....	None
Volume Solids.....	57±2%
Specific Gravity.....	1.2±0.05 gr/cm ³
Flash Point.....	27°C
Dry Film Thickness.....	20-40 microns
Touch dry.....	2-4 hrs at 20°C
Hard dry (fully cured).....	7 days at 20°C
Thermal Resistance.....	140°C
Theoretical coverage.....	28.5-14.25
sqm/lit.	23.75-11.87
sqm/kg	
Practical Coverage.....	Depends on loss factor
Shelf life	1 year at 25°C

APPLICATION DETAILS

Application method	Air/Airless spray, Bursh
Nozzle orifice.....	.017"-0.021"
Nozzle pressure.....	100 bar/1450 Psi
Application temperature.....	10-50°C
Mixing ratio.....	4/1 by weight
Thinner/Cleaner.....	SVT-87
Pot life	8 hrs at 20°C
Recoat interval.....	Min 6 hrs at 20°C
	Max none

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار