

## SARV RANG PRODUCT DATA SARV COAT 8735 EPOXY POLYAMIDE INTERMEDIATE COATINGS



### DESCRIPTION

Sarv coat 8735 is a two component, polyamide cured epoxy intermediate coat.

### OUTSTANDING CHARACTERISTICS

- Excellent oil resistance.
- Excellent chemical resistance against weak acids and alkalies.
- Suitable as 2nd coat in various epoxy paint systems.
- Corrosion resistance in moderately to severely environment.

### RECOMMENDED USE

As a protective intermediate coat in industrial and marine structures, over concrete or metal surfaces.

### SURFACE PREPARATION

The surface must be clean and dry, All dirt, grease, mill- scales and other foreign materials should be removed. Old primed surfaces must be smoothly wire brushed.

### PHYSICAL DATA

Finish.....	Semi Flat
Colour.....	Upon request
Volume Solids.....	63%
Specific Gravity.....	1.40 kg/L
Flash Point.....	30°C
Recommended D.F.T.....	125 microns
Theoretical coverage.....	5.0 m <sup>2</sup> /L at 125 microns
Practical Coverage.....	Depends on loss factor
Touch dry.....	2 hrs at 20°C
Fully cured.....	7 days at 20°C
Thermal Resistance.....	140 °C
Shelf life.....	1 year at 25°C
Package.....	5 & 20 liter container

### APPLICATION DETAILS

Application method .....	Air/Airless spray, Brush
Nozzle orifice.....	..021”
Nozzle pressure.....	150 bar/2200 Psi
Mixing ratio.....	Base / Hardener 4/1 by weight
Thinner/Cleaner.....	SVT-87
Pot life .....	8 hrs at 20°C
Recoat interval min:.....	24 hrs at 20°C
Recoat interval max:.....	14 days at 20°C

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6  
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار