

SARV RANG PRODUCT DATA SARV COAT 8824-7 EPOXY POLYAMINE HIGH BUILD ABRASION RESISTANT COATINGS



DESCRIPTION

Sarv coat 8824-7 is a two component, polyamine cured, high build epoxy coating silicium oxide as reinforcing ingredient.

OUTSTANDING CHARACTERISTICS

- Excellent abrasion resistance.
- Excellent chemical resistance against weak acids and alkalies.
- Corrosion resistance in moderately to severely marine & industrial environment.

RECOMMENDED USE

As a high build, high performance protective coating in aggressive environment over concrete or metal surfaces where a non skid & abrasion resistant surface is needed.

SURFACE PREPARATION

The surface must be clean and dry. All dirt, grease, mill- scales and any other foreign materials should be removed.

PHYSICAL DATA

Finish.....	Flat
Colour.....	Upon request
Volume Solids.....	85 %(ASDM-D 2697)
Specific Gravity.....	1.31 kg/L
Flash Point.....	30°C
Reconnended D.F.T	150 microns /percoat
Thermal coverage.....	6.8 m ² /L
Practical Coverage.....	Depends on loss factor
Touch dry.....	6 hrs at 20°C
Hard dry.....	7 days at 20°C
Thermal Resistance.....	140°C
Shelf life	1 year at 25°C

APPLICATION DETAILS

Application method	Air/Airless Spray Bursh
Nozzle orifice.....	.021"
Nozzle pressure.....	150 bar/2200 Psi
Application temperature.....	5-50°C
Thinner/Cleaner.....	SVT-88
Pot life	2 hrs at 20°C
Recoat interval.....	Min 24 hrs Max 72 hrs

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار