

# SARV RANG PRODUCT DATA SARV COAT 8824 EPOXY POLYAMINE GLASS FLAKE COATINGS



## DESCRIPTION

Sarv coat 8824 is a two component, polyamine cured, high build glass flake epoxy coating.

## OUTSTANDING CHARACTERISTICS

- Excellent mechanical strength
- High resistance against crude oil.
- High chemical resistance against weak acids and alkalies.
- Applicable in high film thickness.
- High sea water resistance or use in splash and tidal zone.

## RECOMMENDED USE

As a epoxy coating with excellent chemical & mechanical properties, suitable for coating chemical products containers and industrial or marine structures.

It protects both steel and concrete structures in severe environments including marine structures petroleum and heavy industrial facilities.

## SURFACE PREPARATION

Remove and oil, grease and other, other contaminants by detergent and salt high pressure fresh water hosing prior to water hosing prior to abrasive blasting.

Abrasive blasting to Sa2½ ( ISO 8501-1:1988) with a surface profile equivalent to regotes No. 3 BN 10b, Keane- tator compactor 3.0 G/S ISO compactor, rough Medium. (G)

## PHYSICAL DATA

Finish.....	Semi gloss
Colour.....	limited
Volume Solids.....	68 ± 2 %
Weight solid .....	80 ± 2
Specific Gravity..... (Mixed)	1.3±0.05 gr/cm <sup>3</sup>
Flash Point (closed cup).....	32°C
Touch dry.....	10 hrs at 20°C
Hard dry.....	1 week at 20°C
Dry film thickness.....	300 microns
Theoretical coverage.....	2.36 sqm/lit 1.74 sqm/kg
Practical Coverage.....	Depends on loss factor
Shelf life .....	1 year at 25°C

## APPLICATION DETAILS

Application method .....	Airless 1:60 (See Remark over leaf)
Nozzle orifice.....	.035"-.045" reversible
Nozzle pressure.....	250 bar/3600 Psi
Mixing ratio.....	Base/Hardener 6/ 1 by weight
Thinner/Cleaner.....	SVT-88
Pot life .....	1 hrs at 20°C

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6  
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار