

## SARV RANG PRODUCT DATA SARV COAT 8828-8 EPOXY POLYAMINE ANTI-STATIC PRIMER COATINGS



### DESCRIPTION

Sarv coat 8828-8 is a two component, polyamine cured epoxy anti static primer.

### OUTSTANDING CHARACTERISTICS

- Excellent mechanical strength.
- High chemical & solvent resistance
- High electrical conductivity
- Easy application

### RECOMMENDED USE

As a primer coat on concrete, floors subjected to electrical conductivity.

### SURFACE PREPARATION

The surface must be clean & dry. All dirt, Grease, mill scales and any other foreign materials should be removed.

### PHYSICAL DATA

Finish.....	Semi Gloss
Colour.....	Black
Volume Solids.....	65 %
Specific Gravity.....	1.20±0.05 gr/cm <sup>3</sup>
Flash Point.....	30°C
Dry Film Thickness .....	40-60 microns
Touch dry.....	2 hrs at 20°C
Hard dry.....	1 week at 20°C
Thermal Resistance.....	140°C
Thermal coverage.....	17.25-11.5 sqm/lit
.....	13.8-9.25 sqm/kg
Practical Coverage.....	Depends on loss factor
Shelf life .....	1 year at 25°C

### APPLICATION DETAILS

Application method .....	Bursh, Trowel
Application temperature.....	10-50°C
Mixing ratio.....	Base / hardener/5/1 by weight
Thinner/Cleaner.....	SVT-88
Pot life .....	90 min at 20°C
Recoat interval.....	Min 24 at 20°C
	Max 72 hrs at 20°C

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6  
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار