

SARV RANG PRODUCT DATA SARV COAT 8831 EPOXY POLYAMINE PUTTY COATINGS



DESCRIPTION

Sarv coat 8831 is a two component, polyamine cured, solvent free epoxy putty.

OUTSTANDING CHARACTERISTICS

- Excellent mechanical strength
- High oil resistance
- High chemical resistance against acids and alkalis.
- Applicable in high film thickness.

RECOMMENDED USE

As a solvent free epoxy coating with excellent chemical & mechanical properties, suitable for coating chemical products containers and industrial or marine structures.

SURFACE PREPARATION

The surface must be clean and dry. All dirt, grease, millscals and any other foreign materials should be removed.

PHYSICAL DATA

Colour.....	upon request
Volume Solids.....	99±1%
Specific Gravity.....	1.85±0.05 gr/cm ³
Flash Point.....	65°C
Touch dry.....	5 hrs at 20°C
Hard dry.....	1 week at 20°C
Thermal Resistance.....	140°C
Shelf life	1 year
Package.....	20& 20 liter container

APPLICATION DETAILS

Application method	knife
Application temperature.....	5-50°C
Mixing ratio.....	1/1 by weight
Thinner/Cleaner.....	SVT-88
Pot life	1 hrs at 20°C
Recoat interval.....	Min 24 hrs Max 72 hrs

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6

کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار