

# SARV RANG PRODUCT DATA SARV COAT 9520 POLYURETHANE SEALER COATINGS



## DESCRIPTION

Sarv coat 9520 is a two component, isocyanate cured aliphatic polyurethane sealer.

## OUTSTANDING CHARACTERISTICS

- Excellent penetration
- High chemical & solvent resistance.
- With the proper topcoat it withstands splash or spillage of water.

## RECOMMENDED USE

For use on concrete, metal surfaces and as an intermediate coat on zinc silicates to minimize popping.

## SURFACE PREPARATION

Sand blasting or wire brushing to a standard of ST2(SA 2.5, SIS 05 5900 ISO 8501-1). For concrete and previously primed surfaces with sarv coat 1983, the surface must be clean and dry. All dirt, grease, mill-scales and any other foreign material should be removed.

## PHYSICAL DATA

Finish.....	Flat
Colour.....	Non pigmented
Volume Solids.....	40±2%
Specific Gravity.....	1.0 ±0.02 gr/m <sup>3</sup>
Flash Point.....	30°C
Dry Film Thickness.....	20-30 microns
Touch dry.....	5 hrs at 20°C 3hrs at 35°C
Fully cured.....	1 week at 20°C 5 days at 35°C
Thermal Resistance.....	120°C
Shelf life.....	1 year at 25°C
Package.....	4& 20 liter container

## APPLICATION DETAILS

Application method .....	Air/Airless spray, Brush
Nozzle orifice.....	.017"-0.019"
Nozzle pressure.....	150 bar/2200 Psi
Mixing ratio.....	Base/Hardener 5/1 by weight
Thinner/Cleaner.....	SVT- 95
Pot life .....	5 hrs at 20°C
Recoat interval min:.....	16 hrs at 20°C
*Recoat interval max:.....	none withitself

دفتر مرکزی: تهران، آیت الله کاشانی، ابتدای جنت آباد جنوبی، نیش کوچه پاستور، ساختمان سهیل، واحد 5 و 6  
کد پستی: 1473913774

تلفن: 44037532 - 44037534 - 44486491 - 44043081 - 44045187

فکس: 44037529 ایمیل: sarvrang.co@gmail.com

آدرس کارخانه: جاده خاوران، کیلومتر 9 شریف آباد، بعد از شهرک صنعتی عباس آباد، انتهای بلوار نگار